


A STYLISH SUEDE DECORATIVE PLASTER THAT EMBODIES BOTH CHARACTER AND AMBIENCE. THIS RESIN BONDED PLASTER PROVIDES A SEAMLESS FINISH WHICH, WHILE AESTHETICALLY PLEASING, ALSO OFFERS SUPERIOR PROTECTION OF THE SUBSTRATE.



PRODUCT INFORMATION

- Suitable for interior or exterior use on either new or previously painted walls that have been properly prepared.
- Applied to a coating thickness of 1.5mm to 2.0mm throughout.
- Tinted to a wide colour range.
- Accentuate design elements through imaginative paneling and the creation of contrasting bands. We strongly recommend the use tape joints to create paneling and so to avoid dry joints, this is particularly important when applying the product over a large area.
- May be sealed with a glaze to further enhance and protect.
- Eco friendly, water based, LOW VOC LEVEL [19g/L]
- Made to order, supplied ready to use.
- Trowel application.



UNIQUE INTERNATIONAL GUARANTEE

MARMORAN 10 YEAR INTERNATIONAL GUARANTEE UNDERWRITTEN BY A THIRD PARTY is issued on condition that the system is applied by a Marmoran Licenced Applicator in strict accordance to the full specification and is accepted and signed by the relevant parties. Due to the demand for the highest standard of application and finish, it must be applied by a trained applicator that is skilled and experienced.

PRODUCT CODE AS024

PRODUCT DATA INFORMATION SHEET

TESTED TO NATIONAL & INTERNATIONAL STANDARDS BY THREE INDEPENDENT LABORATORIES

TEST STANDARDS

| | |
|-------------------|---|
| ASTM D4828 | Easily cleaned up to 10,000 scrubs without exhibiting wear or signs or loss of adhesion |
| CGRI/R+H | Superior quality pure acrylic resin ensures resistance to dirt pickup |
| ASTM 4060 | Tough & durable with high resistance to abrasion & scuffing |
| ASTM G53 | UV resistant to prevent excessive chalking, colour change, flaking or peeling |
| ISO 1519 | Exhibits outstanding flexible qualities, yet hard and durable to withstand the stresses of natural expansion and contraction of the substrate |
| ASTM E96 | Controlled water vapour permeability allows the walls to “breathe” to maintain resistance to water ingress and prevent spalling, delamination, algae and dirt retention |
| ISO 2409 | Superior adhesion to all suitably primed substrates |
| SABS 170 | Excellent resistance to alkali salts to prevent coating delamination and adhesion |
| SABS 1586 | Ability to withstand high temperatures with no signs of delamination, blistering or loss of adhesion |
| SABS 146 | Excellent impact resistance and tensile strength |
| ISO 12040 | Exceptional weathering, water repellency and ultraviolet resistant properties |

USES

- Designed for interior or exterior use as a protective and decorative coating for a wide variety of new or previously coated surfaces that have been suitably prepared and primed. This includes cement plasters, concrete, fibre cement, ceiling boards, off shutter concrete, highly porous surfaces, gypsum, timber and steel.
- This product is particularly suitable to accentuate design elements of a structure due to its unique reflective glitter pigment and through imaginative paneling and the creation of contrasting bands.

COLOUR

- Available in a wide colour range

PACKAGING

- 8, 32 and 300 kg containers

GENERAL CONSIDERATION REGARDING APPLICATION

SITE SURVEY REPORTS

Site Survey Reports and Records are to be completed prior to product application, during the application and on completion of the project so that the relevant documentation is available for processing the Guarantee.

CLIMATIC CONDITIONS

Adequate protection should be provided against rain and sub-zero temperatures for a period of not less than 24 hours after application. The coating should never be applied during adverse weather conditions, or on wet surfaces. Even if the weather seems fit, there may be condensation if the temperature of the substrate is at or below the dew point (temperature at which the atmospheric humidity condenses e.g. as dew) the product should only be applied when the temperature of the substrate is at least 2 deg C above dew point. In hot climates, the coating should be applied during the morning and late afternoon hours and if possible away from direct sunlight. Variations in temperatures will affect drying times.

APPLICATION

- The product must be applied in strict accordance to the Manufacturer's System and Specification.
- Please refer to our notes on **BEST PRACTICES FOR SURFACE PREPARATION**.
- **Inspect the substrate** The plaster should be a fine wood float finish and adequate time should be allowed for it to cure [confirm a moisture reading of <15%: this may take from 7-21 days, depending on weather conditions] prior to the application of any specialised, semi-specialised coating or paint.
- **Prepare the substrate** appropriately to ensure that the surface is clean, dry and sound.
- Ensure that the **scaffold** be positioned at a comfortable distance away from the surface so that application technique is not compromised. (400-600mm).
- **Sealing of expansion/control joints:** we recommend the use of sealant compatible with the specified Marmoran product, a suitable Marmoran Primer may then be applied directly over these joints.
- **We strongly recommend the use tape joints to create paneling and so to avoid dry joints, this is particularly important when applying the product over a large area.**
- **Batch control** it is the responsibility of the contractor to ensure colour consistency. It is recommended that sufficient material to complete the project be ordered where possible to eliminate possible colour variation. Where this is not practical, sufficient material to complete an elevation should be ordered with any excess used as the first coat on the subsequent elevation.
- **Check** spread rates, tools and patterning.
- The product is **supplied ready for use. DO NOT THIN.**

APPLICATION METHOD

- **Apply** 1 even coat of the appropriate **Marmoran Primer** and allow to cure. We recommend the use of a primer such as Marmoran Universal Primer where the substrate is non porous or dense (i.e. off shutter concrete) followed either by Marmoran RBP Textured Acrylic Primer or Marmoran RLP Textured Acrylic Primer where there is a distinct colour difference between the Marmoran Permasuede and the surface to be coated.
- **Marmoran Permasuede** is applied with a steel trowel. A 6mm notch trowel is then used to obtain a uniform thickness and to remove the excess. The product is then flattened with a steel trowel. Allow the product to flash off, and then pattern with a steel trowel (a busier pattern can be achieved by using a plastic trowel)
Flash off Time: this is the time taken for the product to touch dry before patterning. This time is critical - *if the product is not allowed to flash off, the desired pattern will not be achieved.* Flash off time at a thickness of 1.5 to 2.0 mm is about 15-30 minutes, temperature dependant. A thicker coating will require a longer flash off time.
- **Optional:** if required apply a **Marmoran Glaze Coat** [Marmoran Universal Glaze (Exterior) or Marmoran Supaglaze (Interior)] to seal and protect the coating. Crosshatch to achieve complete obliteration. Allow for drying time between coats. For further information please refer to the relevant Technical Data Sheet.
- The system must be applied in strict conformance to the manufacturers' instructions.

SPECIFICATION FOR MARMORAN PERMASUEDE SYSTEM

NEW WORK

Inspect the substrate, the plaster should be a fine wood float finish and adequate time should be allowed for it to cure prior to the application of any specialised, semi-specialised coating or paint.

Prepare the substrate appropriately to ensure that the surface is clean, dry and sound.

Apply an even coat of the appropriate **Marmoran Primer**

Apply the **Marmoran PERMASUEDE SYSTEM** [ASTM E96 Compliant: Controlled Water Vapour Permeability] to match the approved colour & pattern of **Marmoran Sample Panel Reference Number: S/_____**

If required apply an even coating of **Marmoran Glaze**.

This Marmoran Coating System Has A 10 Year International Guarantee Underwritten By A Third Party.

It is issued on condition that it has been applied by a Marmoran Licenced Applicator in strict accordance to the full specification and is accepted and signed by the relevant parties. Due to the demand for the highest standard of application and finish, it must be applied by a trained applicator that is skilled and experienced

REDECORATION

Prepare the surface by removing all loose and flaking paint, dirt, grease and grime. Make good all cracks and defects and then repair and prime to match the existing surface. Proceed as for new work.

PRODUCT DATA

Composition Inert Pigments, Fillers and additives dispersed in an Acrylic Copolymer Resin.

Solvent Type Water

Solids **Volume** 75% ± 2% **Mass** 86% ± 2%

VOC LEVEL **19g/L [0.99 %]** white, pastel & medium colours.

The International GREEN SEAL STANDARD is 150g/L [11.5%] for non flat coatings.

Drying Times **Surface Dry:** 2 hours **Hard Dry:** 12 hours **Over coating Time:** 6hours

@ 25 deg C, Higher temperatures will accelerate the drying times (approximately halved for every 10 deg C increase)

65% RH Lower temperatures will retard the drying times (approximately doubled for every 10 deg C decrease)

Theoretical 2.5 to 3.0 kg / m² at a thickness of ± 1.5mm

Spread rate This figure is indicative, and subject to applicator skill and substrate type and condition.

Actual spread rates must be determined by the Applicator.

Shelf life & Storage 6 - 8 Months in unopened containers. Store in a cool dry and well ventilated place away from excessive heat or an open flame. Do not allow to freeze.

Transport Non hazardous in accordance with Transportation and Classification of Dangerous Goods Act (1996)

Handling & Safety This product is water based and non-toxic. Keep out of reach of children. It does contain chemicals that may be irritants to mammalian tissue. Appropriate protective clothing must be worn. Protect eyes and skin from exposure. If the product is being sprayed, ensure adequate ventilation and ensure the use of proper ventilated masks. Wash spillages immediately with water. Do not induce vomiting if swallowed. Consult a physician if irritation of skin persists or if product is ingested. Gather up environmental spillages, and dispose of in accordance with regulations of the local authorities.

Disclaimer All information contained herein is given in good faith, based on our specialised knowledge and experience.

We reserve the right to effect changes to product and specification alike in the interest of product development and improving technology.